Stockholm University

This is an accepted version of a paper published in *Journal of Alloys and Compounds*.

Citation for the published paper:

Fahlquist, H., Kadir, A., Noréus, D. [Year unknown!]

"Structural characterization of $\text{Sr}_4\text{Mg}_4\text{H}_4[\text{CoH}_5]_3$ shows the importance of support from polarizing counter ions to 3d transition metal hydrido complexes"

Journal of Alloys and Compounds

Access to the published version may require subscription.

Permanent link to this version:

<http://urn.kb.se/resolve?urn=urn:nbn:se:su:diva-89755>

<http://su.diva-portal.org>

Manuscript Number: JALCOM-D-13-01972R1

Title: Structural characterization of $\text{Sr}_4\text{Mg}_4\text{H}_4[\text{CoH}_5]_3$ shows the importance of support from polarizing counter ions to 3d transition metal hydrido complexes

Article Type: Letter

Keywords: metal hydrides, transition metal alloys and compounds, chemical synthesis, crystal structure,

Corresponding Author: Prof. Dag Noreus,

Corresponding Author's Institution:

First Author: Henrik Fahlquist

Order of Authors: Henrik Fahlquist; Karim Kadir; Dag Noréus

Abstract: The structure of the title compound was refined from neutron powder diffraction data in the cubic space group $P-43m$ (215). The unit cell contains one formula unit with 3 structurally equivalent $[\text{Co}(\text{I})\text{H}_5]^{4-}$ complexes as well as 4 interstitial hydride (H^-) ions. The presence of the larger and less polarizing Sr^{2+} ions weakens the bond in the complexes and probably also the stability of the structure. Attempts to synthesize the corresponding Ba analogue failed in contrast to using smaller and more polarizing Ca^{2+} and Yb^{2+} counterions.

Dear Professor Buschow
Editor
Journal of Alloys and Compounds

Thank you for considering publishing our paper.

We have amended our paper according to the suggestions from the reviewer as follows:

We added a Figure 1 that shows the refinement of the NPD data with a difference plot and the refined content of impurity phases.

We added a Figure 2 that shows the most important part with the CoD5 complex in its surrounding distorted cube. The full structure has already been published in the references. In the article we have also made a more detailed comparison with the same surrounding in the in the related AeMgNiH₄ series (Ae = Mg, Ca, Sr).

The title has been shortened and a corrected CHI2 value taken from the CIF-file.

With this we hope the paper has become acceptable.

Yours sincerely

Dag Noréus

Structural characterization of $\text{Sr}_4\text{Mg}_4\text{H}_4[\text{CoH}_5]_3$ shows the importance of support from polarizing counter ions to 3d transition metal hydrido complexes.

Henrik Fahlquist, Karim Kadir and Dag Noréus
Department of Materials and Environmental Chemistry, Stockholm University,
SE-106 91 Stockholm, Sweden

Abstract

The structure of the title compound was refined from neutron powder diffraction data in the cubic space group P-43m (215). The unit cell contains one formula unit with 3 structurally equivalent $[\text{Co}(\text{I})\text{H}_5]^{4-}$ complexes as well as 4 interstitial hydride (H^-) ions. The presence of the larger and less polarizing Sr^{2+} ions weakens the bond in the complexes and probably also the stability of the structure. Attempts to synthesize the corresponding Ba analogue failed in contrast to using smaller and more polarizing Ca^{2+} and Yb^{2+} counterions.

Introduction

Hydrogen rich transition metal (TM) hydrido complexes can be formed with the help of valence electrons from electropositive alkali and alkali earth metals if they are reacted together in the presence of hydrogen. The bonds in the complexes have a predominantly sd-character, making the 4d- and 5d TM-complexes fairly strong as the soft 4d- and 5d-electrons fit well with the soft and polarisable hydride ligand.¹ There has been a large number of metal hydrides synthesised with such complexes synthesised to date both with alkali and alkaline earth counter ions. There are now several examples such as A_4TMH_6 ($\text{A}=\text{Li}, \text{Na}, \text{TM}=\text{Ru}, \text{Os}$), Ae_2TMH_6 ($\text{Ae}=\text{Mg}, \text{Ca}, \text{Sr}, \text{Ba}, \text{TM}=\text{Ru}, \text{Os}$), A_2PdH_2 ($\text{A}=\text{Li}, \text{Na}$), K_2PdH_4 and plenty more.²⁻⁵ Corresponding hydrides based on 3d-electrons are rarer as 3d electrons are harder and have more difficulty to bind with the soft hydride ligand. Most of these hydrides have been synthesised with strongly polarizing Mg^{2+} -ions in the counter ion framework, either alone or in combination with other alkali and alkali earth counterions. This is especially so for the most d-electron rich TMs cobalt and nickel, where no hydrido complex has been synthesized without Mg^{2+} ions in the counterion framework. Here Mg^{2+} has a role beyond a simple counter ion in solid state hydrides, as it helps to relieve some of the electron density via the very polarisable hydride ions, thus strengthening the complexes.^{1, 6} In solids state hydrides the effect substitute for the more conventional “back bonding” of electron density to ligand orbitals. In a way this is unfortunate for all the efforts trying to destabilize magnesium hydride (MgH_2) for hydrogen storage by alloying it with nickel, which the well investigated Mg_2NiH_4 system is an example of. Mg_2NiH_4 becomes only marginally less stable than MgH_2 .

A possible way to further reduce the stability could be to partially substitute magnesium with a softer and less polarizing counter ion. This gave a less stable hydride in $(\text{NaMgH})_2\text{NiH}_4$.⁷ At present this has little practical implications as the more stable Mg_2NiH_4 phase reforms when $(\text{NaMgH})_2\text{NiH}_4$ was heated to release hydrogen. But if this can be avoided, it might open up for more practical hydrogen storage systems. Another interesting aspect of lattice effects upon this solid state stabilization of d electron rich complexes is that it creates interesting electric conductivity phenomena. Small disturbances in the counter ion lattice have strong impact on the band gaps and the hydrides can switch from conducting to non-conducting by the use of mechanical strain.^{8,9} We thus believe that it is interesting to further study how substitution in the counter ion frame works influence the stability of these d electron rich transition metal hydrido complexes. For this we tried to expand the previous discovered $\text{M}_4\text{Mg}_4\text{Co}_3\text{H}_{19}$ (M=Ca, Yb) series of hydrides featuring the same d^8 electron $[\text{CoH}_5]^{4-}$ complex as in Mg_2CoH_5 ,^{10,11} by exchanging Ca and Yb with the larger and softer alkali earth metals strontium and barium. We can now report how the $[\text{CoH}_5]^{4-}$ complexes changes as a result of the corresponding strontium substitution in $\text{Sr}_4\text{Mg}_4\text{Co}_3\text{H}_{19}$. But interestingly we could not make the corresponding barium analogue.

Experimental details

Synthesis

All sample handling was performed inside an argon filled glove box with continuously purified atmosphere in order to prevent the reagents and samples from reacting to oxygen and moisture.

$\text{SrH}_2(\text{D}_2)$ and $\text{Mg}_2\text{CoH}_5(\text{D}_5)$ were prepared in advance by treating lumps of Sr(ABCR 99%) in 30 bar $\text{H}_2(\text{D}_2)$ at a temperature of 573K and black coloured $\text{Mg}_2\text{CoH}_5(\text{D}_5)$ was made by heat treatment of pelletized $\text{MgH}_2(\text{D}_2)$ and Co metal powder (Sigma Aldrich 99.8%) in the molar ratio 2:1 under a gas pressure 70 bars at 773 K for 18 hours in a corundum crucible inside a stainless steel autoclave. A K-type thermo couple in a steel capillary was attached to the samples for temperature monitoring.

$\text{Sr}_4\text{Mg}_4\text{Co}_3\text{H}_{19}$ was synthesized by mixing powders of SrH_2 , Co and Mg_2CoH_5 in the molar ratio 4:1:2. The powders were ground using pestle and mortar, and pelletized. The pellet was put in a corundum crucible and placed in a stainless steel autoclave with attached K-type thermo couple for temperature monitoring. The autoclave was pressurized at 60 bar H_2 gas and heated in a tube furnace to 873 K over night.

The pellet was extracted from the autoclave, crushed and analyzed by powder X-ray powder diffraction to observe eventual impurities. A deuterated sample for neutron diffraction was synthesized the same way by using deuterium.

X-Ray and neutron diffraction

Samples were characterized by X-ray powder diffraction at room temperature using a Panalytical X'pert Pro diffractometer with $\text{CuK}\alpha_1$ radiation equipped with a Ge[111] monochromator ($\lambda=1.540598 \text{ \AA}$). The pattern showed the presence of a new quaternary hydride phase having the refined cubic cell parameter $a=6.9408(1) \text{ \AA}$. The metal positions were refined using the initial positions of $\text{Ca}_4\text{Mg}_4\text{CoH}_{19}$. Neutron diffraction was obtained at the TOF instrument GEM at ISIS using a 4 gram sample in a vanadium can $\phi=6\text{mm}$ sealed by indium wire. The structure refinement was performed in GSAS by least squares Rietveld refinement.¹² Figure 1 shows a refined neutron diffraction pattern with a difference plot. The initial deuterium structure factors were obtained from $\text{Ca}_4\text{Mg}_4\text{CoD}_{19}$. The refined unit cell parameter and atomic positional parameters can be found in Table 1 and 2. As in the earlier published $\text{Ca}_4\text{Mg}_4\text{CoD}_{19}$ and $\text{Yb}_4\text{Mg}_4\text{CoD}_{19}$ we could confirm half occupancy for the apical Co-ligand D1, caused by orientational disorder. Interatomic distances and angles are presented and compared to those of $\text{Ca}_4\text{Mg}_4\text{CoD}_{19}$ and $\text{Yb}_4\text{Mg}_4\text{CoD}_{19}$ in Table 3.

Results and discussion

It is interesting to compare the Co-D distances in this work with those in $\text{Ca}_4\text{Mg}_4\text{Co}_3\text{D}_{19}$, $\text{Yb}_4\text{Mg}_4\text{CoD}_{19}$ and Mg_2CoD_5 . The Co-D distances elongate indicating a weaker bond, when substituting magnesium with strontium compared to using ytterbium or calcium or to the corresponding distances in Mg_2CoD_5 .

Strontium is larger and less polarizing than both ytterbium and calcium, which both have similar polarizability. In addition to the 15 hydrogen ligands on the three $[\text{CoD}_5]^{4-}$ complexes there are 4 interstitial hydride ions (D3) in a tetrahedral site. The apical Co-D2 distance is significantly longer than the Co-D1 distance but it is also significantly longer than the apical Co-D distance in Mg_2CoD_5 . The interstitial deuteride anions (D3) are tetrahedral coordinated by 3 Sr atoms and 1 Mg atom with the distances $\text{D3-Sr} = 2.502(3) \text{ \AA}$ and $\text{D3-Mg} = 1.877(4) \text{ \AA}$. The D3-Mg distance is significantly shorter than the ones reported in $\text{Ca}_4\text{Mg}_4\text{Co}_3\text{D}_{19}$ and $\text{Yb}_4\text{Mg}_4\text{CoD}_{19}$, $\text{Mg-D} = 1.956(6)$ and $1.945(7)$ respectively. It is also significant shorter than the Mg-D distance in MgH_2 , $1.98 \text{ \AA}$. This is probably due to the lower electronegativity of strontium (0.95) compared to calcium (1.0) and ytterbium (1.1). Figure 2

depicts the $[\text{CoD}_5]^{4-}$ complex sitting within a distorted cube with Mg^{2+} and Sr^{2+} ions in alternating corners. The same arrangements can interestingly also be found in the AeMgNiH_4 series ($\text{Ae} = \text{Mg}, \text{Ca}, \text{Sr}$).¹³ We also tried to synthesize the corresponding $\text{Ba}_4\text{Mg}_4\text{CoD}_{19}$ but this was not possible, also a corresponding BaMgNiH_4 could not be synthesized as an extension of the AeMgNiH_4 series in spite of significant efforts by the group.¹³ This is probably due to an increasing instability in the structures caused by the lesser polarizing support from the counter ion framework, indicating its importance for stabilizing this type of hydrides.

ACKNOWLEDGEMENT

Funding by the Swedish Energy Agency is gratefully acknowledged.

REFERENCES

- [1] U. Häussermann, H. Blomqvist, D. Noréus, *Inorg. Chem.* **41**, 3684 (2002).
- [2] M. Kritikos, D. Noréus, A. F. Andresen, P. Fischer, *J. Solid State Chem.* **92**, 514 (1991).
- [3] M. Kritikos, D. Noréus, *J. Solid State Chem.* **93**, 256 (1991).
- [4] K. Kadir, M. Kritikos, D. Noréus, A. F. Andresen, *J. Less-Common Met.* **172-174** 36 (1991).
- [5] K. Yvon, G. Renaudin, *Encyclopedia of Inorganic Chemistry*, Second Edition Volume III, pp. 1814–1846 (ISBN 0-470-86078-2) John Wiley & Sons, Ltd, Chichester, 2005
- [6] G. J. Miller, H. Deng, R. Hoffmann, *Inorg. Chem.* **33**, 1330 (1994).
- [7] K. Kadir and D. Noréus, *Inorg. Chem.* **46**, 2220 (2007).
- [8] H. Blomqvist, D. Noréus, *J. Appl. Phys.* **91**, 5141 (2002).
- [9] M. Lelis, D. Milcius, E. Wirth, U. Hålenius, L. Eriksson, K. Jansson, K., Kadir, J. Ruan, T. Sato, T., Yokosawa, D. Noréus. *J. Alloys Compd.* **496**, 81 (2010).
- [10] B. Huang, K. Yvon, P. Fischer, *J. Alloys Compd.* **227**, 116 (1995).
- [11] P. Zolliker, K. Yvon, P. Fischer, J. Schefer, *Inorg. Chem.* **24**, 4177 (1985).
- [12] A. Larson, R. B. von Dreele, *Los Alamos National Laboratory Report* 86–748 (1994)
- [13] . B. Huang, K. Yvon, P. Fischer, *J. Alloys Compd.* **204**, L5-L8, (1994).

Table 1 Refinement parameters for $\text{Sr}_4\text{Mg}_4\text{CoD}_{19}$

Spacegroup, P-43m (215), Z=1
a = 6.91372(8) Å
R_{wp} , % = 3.66 %
Goodness of fit, χ^2 = 6.97 %

Table 2 Atomic parameters for $\text{Sr}_4\text{Mg}_4\text{CoD}_{19}$

Atom	Wyckoff position	Occupancy	x	y	z	U, Å ²
Sr	4e	1	0.7064(4)	0.7064(4)	0.7064(4)	0.0133(9)
Co	3d	1	1/2	0	0	0.009(2)
Mg	4e	1	0.1983(5)	0.1983(5)	0.1983(5)	0.012(1)
D1	12h	1	1/2	0	0.2242(3)	0.0339(8)
D2	6f	0.5	0.2684(8)	0	0	0.030(2)
D3	4e	1	0.3544(3)	0.3544(3)	0.3544(3)	0.011(1)

Table 3 Comparison of interatomic distances and angles for $\text{Sr}_4\text{Mg}_4\text{CoD}_{19}$ with $\text{Ca}_4\text{Mg}_4\text{CoD}_{19}$ and $\text{Yb}_4\text{Mg}_4\text{CoD}_{19}$

	$\text{Sr}_4\text{Mg}_4\text{CoD}_{19}$	$\text{Ca}_4\text{Mg}_4\text{CoD}_{19}^{10}$	$\text{Yb}_4\text{Mg}_4\text{CoD}_{19}^{10}$
Co-D1 x4	1.552(2)	1.546(3)	1.546(5)
D2 ^a x2	1.621(5)	1.586(9)	1.58(1)
Mg x4	2.847(4)	2.750(5)	2.738(5)
Sr x4	3.207(2)	3.110(5)	3.100(2)
Sr-D3 x3	2.502(3)	2.355(6)	2.357(5)
D1 x6	2.528(3)	2.440(5)	2.431(2)
D2 x3	2.880(4)	2.804(5)	2.794(2)
Co x3	3.207(2)	3.110(5)	3.100(2)
Mg x3	3.524(4)	3.422(7)	3.403(6)
Mg-D3	1.877(4)	1.956(6)	1.945(7)
D2 x3	1.991(4)	1.912(5)	1.891(6)
D1 x6	2.504(4)	2.426(5)	2.424(5)
D1-Co	1.552(2)	1.546(3)	1.546(5)
Mg x2	2.504(4)	2.426(5)	2.424(5)
Sr x2	2.528(2)	2.440(5)	2.424(5)
D1 x2	2.195(2)	2.186(3)	2.187(5)
D2 x2	2.244(4)	2.215(7)	2.21(1)
D2 ^a -Co	1.621(5)	1.586(9)	1.58(1)
Mg x2	1.991(4)	1.912(5)	1.891(6)
Sr x2	2.880(2)	2.804(5)	2.794(2)
D1 x2	2.244(4)	2.215(7)	2.21(1)
D2 x2	2.597(5)	2.481(9)	2.48(1)
D3-Mg	1.877(4)	1.956(6)	1.945(7)
Sr x3	2.502(3)	2.355(6)	2.357(5)
D3 x3	2.842(3)	2.532(6)	2.571(6)

^aPosition is half occupied

Figure 1. Observed (crosses) and calculated (line) neutron diffraction intensities and difference plot for $\text{Sr}_4\text{Mg}_4\text{D}_4[\text{CoD}_5]_3$. Tickmarks are from top the main phase, with a refined content of 42 wt%, with impurities $\text{SrMg}_2\text{CoD}_7$, 14 wt%, SrMgD_4 , 39wt% and bottom SrD_2 , 5 wt%.

Figure 2. One of three structural equivalent $[\text{CoD}_5]^{4-}$ complexes in $\text{Sr}_4\text{Mg}_4\text{D}_4[\text{CoD}_5]_3$ within a distorted cube made of alternating Mg^{2+} ions (grey) and Sr^{2+} ions (blue). The complex has a disordered orientation in two directions represented by the red half occupied deuterium position.